Black Pearl NC 75

Performance Data

Visible Light	
Transmitted	72%
Reflected	8%
Glare Reduction	19%
Total Solar Energy	
Transmitted	35%
Reflected	6%
Absorbed	59%
Shading Coefficient	0.61
Solar Heat Gain Coefficient	0.53
"U" Factor	1.02
Ultraviolet Light Rejected	99%
Total Solar Energy Rejected	47%
Infrared Rejection	87%
Infrared Energy Rejected	60%

MADICO®

The Clear Choice for Automotive Film

